

NeoSkin Chemo

12" Powder-Free Sterile Examination Gloves

NeoSkin latex-free, sterile gloves by Medgluv have been tested for resistance to permeation of chemotherapy drugs. These neoprene gloves are perfect for USP 800 standards compliance for pharmacy compounding and sterile processing. It meets and exceed ASTM D6978-05 for use of chemotherapy gloves when handling hazardous drugs.

Characteristics and Overview:

- Comply and perfect for USP 797 and 800 Standards compliance for pharmacy compounding and sterile processing.
- Lot Traceable Sterility and Leak Tested.
- Sterile gloves comply with USP 797 and 800 Standards for compounding sterile chemotherapy solutions
- Meets and Exceeds ASTM D6978 Standards for Resistance to Permeation by Chemotherapy Drugs
- Provide the utmost confidence when preparing and administering chemotherapy or handling chemotherapy waste for disposal.



Item No.	Description	Size	Packaging
MGSE8881	NeoSkin Sterile Pairs	X-Small	100 eaches/box
	Neoprene Exam Glove		10 boxes/case
MGSE8882	NeoSkin Sterile Pairs	Small	100 eaches/box
	Neoprene Exam Glove		10 boxes/case
MGSE8883	NeoSkin Sterile Pairs	Medium	100 eaches/box
	Neoprene Exam Glove		10 boxes/case
MGSE8884	NeoSkin Sterile Pairs	Large	100 eaches/box
	Neoprene Exam Glove		10 boxes/case
MGSE8885	NeoSkin Sterile Pairs	X-Large	100 eaches/box
	Neoprene Exam Glove		10 boxes/case



Glove Specifications:

Brand	NeoSkin
Material	Polychloroprene
Color	Green
Sterility	Sterile
Cuff	Beaded Cuff
Sizes	SM, MD, LG, XL and 2XL
Accelerators	Yes
Chemo Tested	Yes
Glove Interior	Powder-Free
Glove Exterior	Full Textured
Length (inches)	12 in
Palm Thickness (Avg)	6.3 mil
Finger Thickness (Avg)	8.2 mil
Tensile Strength (Mpa)	33 / 28 Mpa
Ultimate Elongation (%)	600 / 550
Pin Hole (AQL)	1.5

*Summary of Chemotherapy Testing Reports - ASTM D6978-05

Drug Name	Average Breakthrough Detection Time
Carboplatin	No breakthrough up to 240 min
Cisplatin	No breakthrough up to 240 min
Cyclophosphamide	No breakthrough up to 240 min
Dacarbazine	No breakthrough up to 240 min
Doxorubicin	No breakthrough up to 240 min
Etoposide	No breakthrough up to 240 min
Fluorouracil	No breakthrough up to 240 min
Ifosfamide	No breakthrough up to 240 min
Methotrexate	No breakthrough up to 240 min
Mitomycin C	No breakthrough up to 240 min
Mitoxantrone	No breakthrough up to 240 min
Paclitaxel	No breakthrough up to 240 min
Vincristine Sulfate	No breakthrough up to 240 min
Carmustine	Not for use with Carmustine
ThioTepa	Not for use with ThioTepa

Quality Standards:

Manufactured in accordance with Quality System ISO 9001.
Exceeds and meets current ASTM Standards:
- D6319, D5151, D1671 & D6978.